

An acid bath for the electrodeposition of glossy gold and gold alloy layers and a gloss additive for same

Claims:

5

10

1. An acid bath for the electrodeposition of glossy gold and gold alloy layers, containing gold and optionally one or more alloy elements in dissolved form and also at least one organic compound as a gloss additive, characterised in that, the bath contains, as a further gloss additive, at least one compound of the general formula



15

in which

Sub B1 m is the number 3 or 4

20

R represents a straight-chain or branched or cyclic alkyl group with up to 20 carbon atoms and, in the event that $m = 4$, also an aryl or heteroaryl group with up to 10 carbon atoms, which may be optionally substituted once or several times with straight-chain or branched alkyl groups with 1 to 14 carbon atoms.

25

2. An electrodeposition bath according to Claim 1, characterised in that, it contains, as a further gloss additive, at least one compound of the formula I in which R is a straight-chain or branched alkyl group with 5 to 12 carbon atoms, preferably a branched alkyl group with 6 to 10

carbon atoms.

3. An electrodeposition bath according to Claim 1 or 2, characterised in that, it contains, as a further gloss additive, the compounds pentyl sulfonate, hexyl sulfonate, heptyl sulfonate, octyl sulfonate, nonyl sulfonate, decyl sulfonate, dodecyl sulfonate, cyclohexyl sulfonate, pentyl sulfate, hexyl sulfate, heptyl sulfate, octyl sulfate, nonyl sulfate, decyl sulfate, dodecyl sulfate, cyclohexyl sulfate or their isomers.

4. An electrodeposition bath according to Claims 1 to 3, characterised in that, it contains 0.01 to 10 g/l, preferably 0.1 to 5 g/l, of a compound of the formula I.

5. Use of compounds of the general formula



in which

m is the number 3 or 4 and

R represents a straight-chain or branched or cyclic alkyl group with up to 20 carbon atoms and, in the event that $m = 4$, also an aryl or heteroaryl group with up to 10 carbon atoms, which may be optionally substituted once or several times with straight-chain or branched alkyl groups with 1 to 14 carbon atoms.

as further gloss additives in acid baths for the electrodeposition of glossy gold and gold alloy layers containing gold and optionally one or more alloy

205040-29460001

Sub
B1

Sub
B1

14

SUB
B1

elements in the dissolved form and also at least one organic compound as a gloss additive.

SUB
B1

6. A process for the electrodeposition of glossy gold and gold alloy layers, characterised in that, deposition takes place from a bath in accordance with Claims 1 to 4 at a pH in the range 3 to 6, preferably 4 to 5.

205040 29460001

An acid bath for the electrodeposition of glossy gold and gold alloy layers and a gloss additive for same

Abstract:

- 5 The invention provides an acid bath for the electrodeposition of glossy gold and gold alloy layers and a gloss additive for same.

By using compounds of the formula I



10 in which

m is the number 3 or 4 and

15 R represents a straight-chain or branched or cyclic alkyl group with up to 20 carbon atoms and, in the event that $m = 4$, also an aryl or heteroaryl group with up to 10 carbon atoms, which may be optionally substituted once or several times with straight-chain or branched alkyl groups with 1 to 14 carbon atoms,

- 20 as a further gloss additive, the current density/working range is extended with a small negative effect when the pH is changed and the current efficiency and deposition performance is increased.